

Permeation breakthrough times according to EN374-3:2003 (minutes)

Glove :

Nitrilite® 93-401

| | Chemical Agent | Breakthrough Time | Protection Index | CAS Number | Notified Body | EN Standard |
|--|---|-------------------|------------------|------------|------------------|-------------|
| | Acetic Acid, Glacial | 6 | 0 | 64-19-7 | Centexbel | 374-3:2003 |
| | Acetonitrile | < 5 | 0 | 75-05-8 | Centexbel | 374-3:2003 |
| | Acrylamide, 40% | > 480 | 6 | 79-06-1 | Centexbel | 374-3:2003 |
| | Ammonium Hydroxide, 25% | 7 | 0 | 1336-21-6 | Centexbel | 374-3:2003 |
| | Butyl Alcohol | 37 | 2 | 71-36-3 | Centexbel | 374-3:2003 |
| | Cyclohexane | 67 | 3 | 110-82-7 | Centexbel | 374-3:2003 |
| | Diesel fuel | > 480 | 6 | 68334-30-5 | Force Technology | 374-3:2003 |
| | Dimethyl Sulfoxide | 10 | 1 | 67-68-5 | Force Technology | 374-3:2003 |
| | Ethanol, 70% | 31 | 2 | 64-17-5 | Centexbel | 374-3:2003 |
| | Ethidium bromide in water (saturated, ± 5%) | > 480 | 6 | 1239-45-8 | Centexbel | 374-3:2003 |
| | Ethyl Acetate | < 5 | 0 | 141-78-6 | Centexbel | 374-3:2003 |
| | Hexane | > 480 | 6 | 110-54-3 | Centexbel | 374-3:2003 |
| | Hydrogen Peroxide, 30% | 22 | 1 | 7722-84-1 | Centexbel | 374-3:2003 |
| | Isopropanol | 81 | 3 | 67-63-0 | Centexbel | 374-3:2003 |
| | Kerosene | 82 | 3 | 64742-81-0 | Force Technology | 374-3:2003 |
| | Methanol | < 5 | 0 | 67-56-1 | Centexbel | 374-3:2003 |
| | Methylmethacrylate | 2 | 0 | 80-62-6 | Force Technology | 374-3:2003 |
| | Perchloroethylene | < 5 | 0 | 127-18-4 | Centexbel | 374-3:2003 |
| | Sulphuric acid, 48% | > 480 | 6 | 7664-93-9 | Centexbel | 374-3:2003 |

Permeation breakthrough times according to EN374-3:2003 (minutes)

| 0 | 1 | 2 | 3 | 4 | 5 | 6 |
|-----------------|-------------------|-------|-------------------|---------|-----------------|-------|
| < 10 | 10-30 | 30-60 | 60-120 | 120-240 | 240-480 | > 480 |
| Not recommended | Splash protection | | Medium protection | | High protection | |

Data given in the table above are based on results of laboratory tests performed on the palm area of the glove or are based on extrapolations from the results of laboratory tests. These tests were run using standard test methods that may not adequately replicate any specific conditions of end use. Because Ansell has no detailed knowledge or control over the conditions of end use, any of these data must be advisory only, and Ansell must decline any liability.

Ansell Healthcare Europe N.V. (European Head Office)

Riverside Business Park, Block J

Boulevard International 55, 1070 Brussels, Belgium

Tel. +32 (0) 2 528 74 00 • Fax +32 (0) 2 528 74 01 • Fax Customer Service +32 (0) 2 528 74 03

<http://www.ansell.eu> • E-mail info@ansell.eu



Permeation breakthrough times according to EN374-3:2003 (minutes)

Glove :

Nitrilite® 93-401

| | Chemical Agent | Breakthrough Time | Protection Index | CAS Number | Notified Body | EN Standard |
|--|---------------------|-------------------|------------------|------------|---------------|-------------|
| | Sulphuric acid, 96% | 8 | 0 | 7664-93-9 | Centexbel | 374-3:2003 |
| | Xylene | < 5 | 0 | 1330-20-7 | Centexbel | 374-3:2003 |

Permeation breakthrough times according to EN374-3:2003 (minutes)

| 0 | 1 | 2 | 3 | 4 | 5 | 6 |
|-----------------|-------------------|-------|-------------------|---------|-----------------|-------|
| < 10 | 10-30 | 30-60 | 60-120 | 120-240 | 240-480 | > 480 |
| Not recommended | Splash protection | | Medium protection | | High protection | |

Data given in the table above are based on results of laboratory tests performed on the palm area of the glove or are based on extrapolations from the results of laboratory tests. These tests were run using standard test methods that may not adequately replicate any specific conditions of end use. Because Ansell has no detailed knowledge or control over the conditions of end use, any of these data must be advisory only, and Ansell must decline any liability.

Ansell Healthcare Europe N.V. (European Head Office)

Riverside Business Park, Block J

Boulevard International 55, 1070 Brussels, Belgium

Tel. +32 (0) 2 528 74 00 • Fax +32 (0) 2 528 74 01 • Fax Customer Service +32 (0) 2 528 74 03

<http://www.ansell.eu> • E-mail info@ansell.eu

